

YBDXX Carbon

Technical Data Sheet 4052

Product Overview

GRAFSTAR™ YBDXX carbon has enhanced properties over those of YBDX carbon and YBD carbon. YBDXX carbon has higher density and mechanical properties, and lower porosity. This material is specially manufactured for electrolysis involving fluorine applications.

Applications

- Anodes for fluorine cells
- Cathodes for fluorine cells
- Electrolysis involving the presence of fluorine

Sizes*

- 2" x 8" x 25.5" rectangles
- 51 mm x 203 mm x 648 mm rectangles
- 2" x 7" x 25.5" rectangles
- 51 mm x 178 mm x 648 mm rectangles

Typical Properties at Room Temperature**

Characteristic	Unit	WG	AG	Unit	WG	AG
Density	lbs/ft ³	103		g/cm ³	1.65	
Maximum Particle Size	inches	0.03		mm	0.76	
Specific Resistance	10 ⁻⁴ Ωin	15.7	18.1	μΩm	40	46
Flexural Strength	psi	3400	3100	MPa	24	21
Young's Modulus	10 ⁶ psi	2.1	1.5	GPa	14	10
Tensile Strength	psi	2600	2000	MPa	18	14
Compressive Strength	psi	15,800	15,800	MPa	109	109
Permeability	Darcy	0.005		Darcy	0.005	
Thermal Conductivity	BTU-ft/hr ft ² °F	3.1	2.7	W/mK	5.1	4.5
CTE (RT to 100 °C)	10 ⁻⁶ /°F	1.4	2.3	10 ⁻⁶ /K	2.5	4.1
Ash Content	%	0.2		%	0.2	
Porosity	%	13		%	13	

Notes:

* Custom lengths also available

** Properties listed are typical and cannot be used as accept/reject specifications

www.graftech.com | grafstar@graftech.com

Redefining limits

United States of America

101 N. Philippi Pike
Anmoore, WV 26323-0120
Ph: +1-800-842-8805
+1-304-624-1253

China

Unit 2104 of International Capital Plaza
1318, Sichuan Road North
Hongkou District, Shanghai China
Ph: +86-21-6325-8018

Italy

Via Forno Allione, 2
1-25040 Malonno, Brescia, Italy
Ph: +39-036-463-0131

France

La Lechere
73264 Aigueblanche Cedex, France
Ph: +33-4-79-41-45-00